

CONIFLOOR 585

2-component, Polyaspartic Topcoat, Pigmented for primed broadcasted surfaces

Product description

CONIFLOOR 585 is a two component, fast polyaspartic topcoat, not yellowing, pigmented for broadcasted surfaces.

Fields of application

CONIFLOOR 585 is used as a coloured top coat to finish the system build-up. CONIFLOOR 585 is used for indoor and outdoor application with low to high mechanical strain.

Properties

CONIFLOOR 585 exhibits high mechanical properties and is easy to apply. Due to its hard and tough properties the coating CONIFLOOR 585 is still slightly elastic, fast curing and UV-stable.

CONIFLOOR 585 is easy to clean and resistant to water, sea and waste water, a variety of alkaline substances, diluted acids, brine, mineral oils, lubricants and fuels.

Technical Data

Mixing ratio	in parts by weight		100 : 69
Density	mix, at 23 °C	g/cm ³	1.36
Viscosity	mix, at 23 °C	mPas	950
Processing time (25 kg working packs)	at 10 °C at 20 °C at 30 °C	min.	30 20 10
Re-coating interval / ready for foot traffic	at 20 °C	minimum h maximum h	8 24
Substrate and application temperature	minimum maximum	°C °C	5 30
Permissible relative humidity	maximum	%	75
Ready for	at 20 °C at 20 °C at 20 °C	d d d	2 1 5
Shore A hardness	after 7d / 23°C		87

Above figures are guide values and should not be used as a base for specifications!

Application method

CONIFLOOR 585 is supplied in the correct proportions of component A (resin) and component B (hardener). Pour component B into component A and ensure that the pail containing component B is emptied completely.

To achieve a homogenous mix, thoroughly mix with a slowly rotating mixing device at about 300 rev/min.

Ensure that the mixing device reaches side and bottom areas of the mixing vessel. The mixing process takes at

least 3 minutes and should be performed until the blend is homogenous and streak free.

Pour the mix into another clean pail and mix it again for 1 additional minute.

The temperature of the components should be between 15-25 °C.

CONIFLOOR 585 can be applied directly to the pre-treated substrate (broadcasted epoxy primer, broadcasted scratch

CONIFLOOR 585 is applied using a rubber squeegee and followed by back rolling.

Working life and curing time of CONIFLOOR 585 are influenced by the ambient and substrate temperature. At low temperatures, the chemical reactions are slowed down; this lengthens the pot life, re-coating interval and open time. High temperature and humidity accelerate chemical reactions so the contrary is true.

To fully cure the material, the substrate and working temperature must not fall below the minimum.

After application, the material should be protected from direct contact with water for approx. 12 hours (at 15 °C). Within this period, contact with water can cause carbamate and/or tackiness on the surface of the coating.

The relative **humidity** level may not exceed **75%**.

Consumption

The consumption rate of CONIFLOOR 585 is approx. 0.6 to max. 0.9 kg/m² and also depend on the grain size of the used silica sand for broad casting (here with size 0.3-0.8 mm). If the grain size 0.6-1.2mm in the system CONIPROOF PES is used, the consumption is min. 0.9 to max. approx. 1.2 kg/m².

Cleaning agent

Re-usable tools should be cleaned carefully with CLEANER 44 or e.g. isopropanol.

Substrate condition

Cement bound substrates to be coated must be firm, dry, load bearing and free of loose and brittle particles and substances, which impair adhesion such as oil, grease, rubber skid marks, paint or other contaminants.

A pre-treatment of the substrate by grit or shot blasting, high pressure water jetting, grinding or scabbing including the necessary post-treatment is mandatory.

After the pre-treatment the bond strength of the concrete must be at least 1.5N/mm².

The **moisture level** must not exceed **4 %**.

The **temperature** of the substrate must be at least **3°C** above the current dew point temperature.

The sub base must contain a moisture barrier (damp proof membrane (D.P.M.).

After the pre-treatment of the substrate the bond strength of the concrete must be at least 1.5N/mm².

Pack size

CONIFLOOR 585 is supplied in 10 kg (metal) working packs. Components A and B are supplied in the correct proportions and delivered separately.

Colour

CONICA AG
Industriestrasse 26
8207 Schaffhausen
Suisse

Tel.: + 41 52 644 3600
Fax: + 41 52 644 3699
info@conica.com
www.conica.com

Whilst any information contained herein is true, accurate and represents our best knowledge and experience, no warranty is given or implied with any recommendations made by us, our representatives or distributors, as the conditions of use and the professional competence involved in the application of the product are beyond our control.

As all CONICA data sheets are updated on a regular basis, it is user's responsibility to obtain the most recent issue. Registered users can obtain the actual data sheets from our webpage. Hard copies are available upon request.

Storage

Store in unopened pails under dry conditions at a temperature range of 15-25 °C.

Do not expose to direct sunlight.

Before use, please see "best before" date on the pail / drum

Safety precautions

CONIFLOOR 585 is non-hazardous in its cured condition.

For protective measures, transport regulations and waste management please refer to the Material Safety Data Sheet of the product.

VOC contents

CONIFLOOR 585 meets the requirements of the EC directive 2004/42/EC.



CE-Label:

See Declaration of Performance.

CE-Mark according to EN 13813

EN 13813: 2003-01, Screed material and floor screeds - Screed materials - Properties and requirements is the basis for requirements for floor screeds used in indoor flooring constructions. Resin coatings and sealer are also subject to this norm.

Details see CE-conformity mark and conformity declaration.